

## TECHNICAL DATA SHEET

# AV-333 INJECTAFLEX™

## HYDROPHILIC POLYURETHANE GROUT

### DESCRIPTION

**AV-333 Injectaflex™** is a single component, mid-range viscosity, moisture-activated polyurethane injection resin designed for sealing active water leaks in various cracks or joints in below-grade structures. **AV-333** has the added benefit of containing dimethyl ketone (acetone) – a highly hygroscopic chemical able to attract surrounding atmospheric moisture and dissolve fats, oils, and greases (FOGs) on contact to ensure good adhesion on various surfaces. **AV-333** cures tough, flexible and closed-cell. Certified for use in potable water.

### APPLICATION

- Midsize cracks or joints in concrete
- Stops infiltration in manholes, basements, retaining walls, etc.
- Use for applications that involve plastics
- Great for applications that are exposed to FOG

### FEATURES AND BENEFITS

- ANSI/NSF/CAN 61 Drinking Water Systems Component Certified
- Mid-range viscosity penetrates well
- Free rise expands 400% – 600%
- Cures tough, flexible and closed-cell with superb adhesive properties
- Contains dimethyl ketone – VOC exempt, hygroscopic, FOG solvent

### GROUTING TECHNIQUES

- Expanded Gasket Placement Technique (EGP)
- Variable Pressure Application Technique (V-PAT)

### HOW IT WORKS

AV-333 reacts in the presence of moisture to form a resilient, flexible seal accomplished by three mechanisms: the resin seeks out water in the space and *adheres* to the surface, then begins to expand forming a tight *compressive* seal while the network of compressed grout material within all the cracks forms a *mechanical* lock. Used via EGP or V-PAT.

### RATIOS

Preferred ratio is 1:1 (water to resin), however no pre-mixing is required. Pumped as a single component.

### PACKAGING

Product packaged by weight based on specific gravity.

Drum	Net Wt. 465 lbs. (211 kg)
Pail	Net Wt. 44 lbs. (20 kg)
Gallon	Net Wt. 8 lbs. (3.6 kg)

### SHIPPING

- Motor Class 55
- Hazard Class 3
- Packing Group II
- Air freight available



### PROPERTIES\*

#### UNCURED

Appearance:	Pale yellow liquid
Viscosity:	350 – 750 cP @ 72°F (22°C)
Flash Point:	-4°F (-20°C)
Specific Gravity:	1.12 @ 72°F (22°C) ±3%
Weight:	9.29 lbs./gal ± 3% (1.113 kg/L ± 3%)

#### CURED

Appearance:	Milky colored, flexible
Tensile Strength:	TBD
Toxicity:	Non-toxic

\*Laboratory Results

### PERFORMANCE

Flush equipment with **AV-208** before and after use to remove moisture and clean equipment. Performance will be influenced by site conditions. If site temperatures are low, heat the product to recommended operating temperatures of 60°F – 90°F (16°C – 32°C). Do not use open flame as a heat source. At temperatures of 45°F (7°C), the viscosity of the product can significantly increase, making the miscibility with the reaction water more difficult.

### CLEANING PRODUCTS

- **AV-208** Technical Grade Acetone™ (CAS# 67-64-1) – removes moisture from equipment (see Performance section).
- **AV-284** Pump Wash™ (Proprietary Blend) – removes uncured resin from pump and hose, leave in pump for storage.
- **AV-222** Cleaner™ (Proprietary Blend) – removes cured resin from equipment.

### STORAGE

Store in temperatures within or near 45°F – 95°F (7°C – 35°C) in a dry, dark atmosphere. Open container slowly to limit degassing. Do not expose to direct sunlight. Keep away from combustible products and open flame. **Note:** storage of opened/partial containers at the lower range of the recommended storage temperature is not advised. The moisture in the air of the head space above a partial container might condensate and causes the grout to premature gel in the container.

### SAFETY

Always use OSHA-approved personal protective equipment (PPE). Refer to the SDS for complete safety precautions. The SDS is available by request or via download at [avantigrout.com](http://avantigrout.com).

### NOTICE

The data, information and statements contained herein are believed to be reliable, but are not construed as a warranty or representation for which Avanti International assumes any legal responsibility. Since field conditions vary widely, users must undertake sufficient verification and testing to determine the suitability of any product or process mentioned in this or any other written material from Avanti for their own particular use. NO WARRANTY OF SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS MADE. In no case shall Avanti International be liable for consequential, special, or indirect damages resulting from the use or handling of this product.

For more information, please contact:  
**ICM of America, Inc**  
**Internet Sales 877-494-5793**



**DRINKING WATER SYSTEM COMPONENT**  
**ANSI/NSF/CAN 61**  
**88NN**